

FLAMMABILITY TEST

Material Test Report

No: 65471

CH.21G.0012

Article/Color: Leder 3503	P/N:	
Description:	Thickness (mm): 1.7	
Composition: Echtleder 100 %		
Customer: Ludwig G. Mannhalter Lederservice	3003657	Test Date: 18.08.2016
Customer PO No: Brandprüfauftrag 10.08.2016	32848	Tested By: Nina Christen

Test Method			Test Requirements		
FAR 25.853 (a), Appendix F, Part I (a) (1), Amdt. 25 / 116 CS 25.853 (a), Appendix F, Part I (a) (1), Amdt. 18			FAR 25.853 (a), Appendix F, Part I, (a) (1) (ii), Amdt. 25 - 116 CS 25.853 (a), Appendix F, Part I, (a) (1) (ii), Amdt. 18		
Flame temperature	Ignition Time	Material Position	Extinguishing Time Max.	Burn Length Max.	Drip Extinguishing Time Max.
>843°C	12 Seconds	Vertical	15 Seconds	203 mm (8 inches)	5 Seconds

Test Results				
Sample No.	Extinguishing Time (Seconds)	Burn Length (mm)	Drip, Extinguishing, Time (Seconds)	Remarks
SAMPLE 1	0,0	10	0,0	no drips
SAMPLE 2	24,8	25	0,0	no drips
SAMPLE 3	2,4	10	0,0	no drips
AVERAGE	9,1	15	0,0	

Test results comply with the requirements of FAR/CS 25.853 Appendix F, Part I, (Amdt. listed above) yes=O / no=N

Lantal Textiles AG certifies that the above mentioned material has been tested in accordance with the terms of the order.
(Unless otherwise stated it is to the specification quoted hereon).

Langenthal 19.08.2016

Signature: 

N. Christen, Lantal Textiles AG